

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 12/26/2001  
 Experimenters: Purav Dave  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Latex binder  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min. immersion cleaning with stir-bar agitation at 120 F  
 Rinsing : 1/2 min. manual in water at 120 F  
 Drying : 1 min. with heat gun at 500 F  
 Contaminant : latex binder mix (00146),  
 CAS# of contaminant : 9016-45-9,7664-41-7, 50-00-0  
 Results: Increase in weight in some cases, decrease in others.

Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Latex binder			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Alconox Inc	Alcojet	1	38.23	<input type="checkbox"/>	Increase in weight in 1 coupon
Buckeye International	Shopmaster FF	5	-15.14	<input type="checkbox"/>	Decrease in weight in only 1 coupon
Buckeye International	Shopmaster HP	5	2.70	<input type="checkbox"/>	Decrease in weight only in 1 coupon
Buckeye International	Shopmaster LPH	5	82.13	<input type="checkbox"/>	in one coupon removal was above 100 percent.
Calgon Corporation	SC 431	5	26.60	<input type="checkbox"/>	
Buckeye International	Immersion Cleaner	5	-9.26	<input type="checkbox"/>	Decrease in weight in 1 coupon
Brulin Corporation	Aquavantage 1400	5	-2.24	<input type="checkbox"/>	Decrease in weight of one coupon

Conclusion: Failure of the test. Bizarre change in weight of the coupons found.