CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2002
DateRun:	01/16/2002
Experimenters:	Purav Dave
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Latex binder
Cleaning Methods:	Ultrasonics
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Degasification: 5 min. in ultrasonic crest at 120 F. Cleaning: 2 min. in ultrasonic crest at 120 F. Rinsing: 1/2 min. manual with water at 120 F. Drying: 1 min. with heat gun at 500 F. Contaminant: Latex binder mix (00146) Cas #: 9016-45-9, 766
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Latex binder				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Alconox Inc	Alcojet	1	95.79	☑	
Buckeye International	Shopmaster LPH	5	107.52	☐	

Conclusion: