CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2002
DateRun:	01/16/2002
Experimenters:	Heidi Wilcox
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Greases
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Immersion: 5-minute immersion soak. Rinsing: Tap water 120 F for 30 seconds. Drying: Heat gun 500 F for 1 minute. Contaminant: Formax Mfr Corp, F-26 grease stick polishing lubricant. (68815-16-7, 67701-27-3, 64742-52-5, 102-71-6)
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Greases				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Kleer Flo Company	Grease Off 2	5	98.77	☑	
Valtech Corporation	Valtron SP 2201	5	95.49	☑	
Valtech Corporation	Valtron SP 2200	5	96.86	☑	
International Products Corporation	LF 2100 (Liquid Foam Cleaner)	5	97.73	☑	
US Polychem Corporation	Polychem PW 147	5	95.35	☑	

Conclusion: