

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 01/03/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
Rinsing: 1/2 min, manual, in 102 F water (tap)  
Drying: 1 min with heat gun @ 500F  
Contaminant: Formax Manufacturing Corp, F-26 grease stick polishing lubricant (solid)

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Greases				
Company Name:		Product Name:	Conc.:	Efficiency:	Effective:	Observations:
AW Chesterton		278 Super Solv	100	97.54	<input checked="" type="checkbox"/>	
Calgon Corporation		Geo Guard 5210	100	52.59	<input type="checkbox"/>	
Fine Organic Corporation		FO 2085 M	5	97.40	<input checked="" type="checkbox"/>	
Oakite Products		Fisan Versaclean	5	99.72	<input checked="" type="checkbox"/>	
Calgon Corporation		Geo Guard 4017	5	100.41	<input checked="" type="checkbox"/>	
Today & Beyond		Beyond 2002	5	99.75	<input checked="" type="checkbox"/>	
Today & Beyond		Beyond 2006	5	97.37	<input checked="" type="checkbox"/>	

Conclusion: All of the cleaners EXCEPT Geoguard 5210 were effective.