

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 05/08/2002

Experimenters: Purav Dave

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Latex binder

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min. immersion cleaning at 120 F. with stir-bar agitation.  
Rinsing: 1/2 min. manual with water at 120 F.  
Drying: 1 min. with heat gun at 500 F.  
Contaminant: latex Binder Mix,  
CAS#: 9016-45-, 79-06-1, 7664-41-7, 924-42-5, 50-00-0, 133386-4, 57-55-6, 7732-18-5

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Latex binder				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Kyzen Corporation	Ionox HC 2	100	46.89	<input type="checkbox"/>		
Safe Science Inc	Heavy Duty Kitchen Cleaner F1	5	54.42	<input type="checkbox"/>		
Safe Science Inc	Heavy Duty Kitchen Cleaner F2	5	33.32	<input type="checkbox"/>		
Sysco Corporation	Heavy Duty Kitchen Cleaner	5	57.28	<input type="checkbox"/>		
Dow Chemical Company	XUS 40570 Development Solvent	100	59.59	<input type="checkbox"/>		
Dow Chemical Company	XUS 40579 Development Solvent	100	54.60	<input type="checkbox"/>		
Oakite Products	Inproclean 61 B		36.25	<input type="checkbox"/>	Cocentration: 20.6g/ml	
Oakite Products	Inproclean 2300		-6.03	<input type="checkbox"/>	Concentration: 426 g/l	
Magnaflux	Daraclean 121	5	23.77	<input type="checkbox"/>		

Conclusion: None of the cleaners were effective.