

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 09/05/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Cutting/Tapping Fluids

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 68 F, ambient  
Rinsing: 1/2 min, manual, in 68F water (tap), ambient  
Drying: 1 min with heat gun @ 500F  
Contaminant: Steco Corp, Tap Magic Protap (cutting fluid)  
CAS# 112-80-1(>75%) Aliphatic organic acid 112-62-9 (<15%) Aliphatic organic ester

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Cutting/Tapping Fluids			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
EcoLink	Bulldog	5	91.32	<input checked="" type="checkbox"/>	
Innovative Organics Inc	Amberclean Q3	5	92.00	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	84.80	<input type="checkbox"/>	
AG Environmental Products	Canola Gold CE110	100	87.57	<input checked="" type="checkbox"/>	
Phase III Inc	California Parts Washer Solution	5	85.41	<input checked="" type="checkbox"/>	
PCI of America	Hurrisafe 9575	5	90.02	<input checked="" type="checkbox"/>	

### Conclusion: