CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2002
DateRun:	10/14/2002
Experimenters:	Heidi Wilcox
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum
PartType:	Coupon
Contaminants:	Adhesive
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F Rinsing: 1/2 min, manual, in 102 F water (tap) Drying: 1 min with heat gun @ 500F Contaminant: Aroset PS 8078, Ashlan Chemical (Lot# 071901). Very thick adhesive CAS#'s 141-78-6 Ethyl Acetate, 142-82-5 Heptane, 67-63-0 Isopropanol
Results:	
Summary:	

Substrates:	Aluminum				
Contaminants:	Adhesive				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
AG Environmental Products	Soy Gold 1000	100	-113.51	☐	
EcoLink	Rip Tide	10	1.69	☐	

Conclusion: