

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003  
 DateRun: 04/01/2003  
 Experimenters: Heidi Wilcox  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Lubricating/Lapping Oils  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
 Rinsing: 1/2 min, manual, in 102 F water (tap)  
 Drying: 1 min with heat gun @ 500F  
 Contaminant: Elf Lubricants Novastone Safeguard 6 Food machinery Lube oil CAS# 64742-47-8, 8042-47-

Results:

Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Lubricating/Lapping Oils			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Florida Chemical Company	Citrus Burst 7	100	58.04	<input type="checkbox"/>	
Florida Chemical Company	D-Limonene	100	72.40	<input type="checkbox"/>	Could increase efficiency by increasing time or changing rinsing and/or drying method
AG Environmental Products	Canola Gold CE110	100	-22.18	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	-22.84	<input type="checkbox"/>	
Vertec BioSolvents	Paint stripper	100	38.67	<input type="checkbox"/>	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	-23.87	<input type="checkbox"/>	
Pentone Corporation	Citrikleen XPC	100	65.64	<input type="checkbox"/>	Increase efficiency by increasing time of cleaning or by changing rinsing and drying method
Vertec BioSolvents	Take Off Green	100	93.99	<input checked="" type="checkbox"/>	

Conclusion: