

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
 DateRun: 03/27/2003
 Experimenters: Jason Marshall
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
 Rinsing: 1/2 min, manual, in 102 F water (tap)
 Drying: 30 seconds air blow off, 68 F
 Contaminant: InstaCure Adhesive CAS# 7085-85-0
 Insta set CAS# 64742-89-8, 99-97-8

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Adhesive			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Metabolix Inc	Metabolix E3HB	100	-49.42	<input type="checkbox"/>	Softened the adhesive but unable to remobe with rinse. May need mor time or energy.
Florida Chemical Company	Citrus Burst 7	100	31.68	<input type="checkbox"/>	adhesive was dripping off with water. A higher pressure rinse may help.
Florida Chemical Company	D-Limonene	100	46.55	<input type="checkbox"/>	adhesive very soft, need better removal method such as a high presure spray
Twin Rivers Technologies	Methyl Ester 1618	100	-74.08	<input type="checkbox"/>	adhesive very soft
AG Environmental Products	Canola Gold CE110	100	-130.75	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	-153.43	<input type="checkbox"/>	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	-80.41	<input type="checkbox"/>	
Pentone Corporation	Citrikleen XPC	100	28.37	<input type="checkbox"/>	
Vertec BioSolvents	Take Off Green	100	65.88	<input type="checkbox"/>	

Conclusion: After cleaning, rinsing and drying, some coupons had a noticeable residue. Wiping was performed to see if efficiencies would increase significantly. Trial 253 shows these results.