

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
 DateRun: 04/01/2003
 Experimenters: Jason Marshall
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Paints
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
 Rinsing: 1/2 min, manual, in 102 F water (tap)
 Drying: 30 seconds air blow off, 68 F
 Contaminant: Glidden Paint Co, Ultra Hide Semi-Gloss
 CAS# 136-52-7, 1317-65-3, 1332-58-1, 6640

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Paints				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Florida Chemical Company	Citrus Burst 7	100	100.24	<input checked="" type="checkbox"/>	
Florida Chemical Company	D-Limonene	100	100.17	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	100.11	<input checked="" type="checkbox"/>	
Brulin Corporation	Nature Sol 100	100	100.24	<input checked="" type="checkbox"/>	
AG Environmental Products	Canola Gold CE110	100	90.94	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Gold 1000	100	84.32	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	76.91	<input type="checkbox"/>	
United Laboratories International	United 2002 Harvest Gold	100	78.46	<input type="checkbox"/>	
Finger Lakes Chemical	2-22 D Limonene Industrial Cleaner	100	97.61	<input checked="" type="checkbox"/>	

Conclusion: