

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 03/28/2003

Experimenters: Jason Marshall

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
Drying: Wiping  
Contaminant: InstaCure Adhesive CAS# 7085-85-0  
Insta set CAS# 64742-89-8, 99-97-8

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Adhesive				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Twin Rivers Technologies	Methyl Ester 1618	100	54.60	<input type="checkbox"/>	
AG Environmental Products	Canola Gold CE110	100	19.02	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	44.94	<input type="checkbox"/>	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	53.00	<input type="checkbox"/>	

### Conclusion: