

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
DateRun: 06/12/2001  
Experimenters: Jason Marshall  
ClientType: Metal  
ProjectNumber: Project #1  
Substrates: Steel  
PartType: Coupon  
Contaminants: Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil  
Cleaning Methods: Ultrasonics  
Analytical Methods: Gravimetric  
Purpose: To evaluate successful cleaners on sixth contaminant.

Experimental Procedure: The four successful cleaners from the previous trial were again diluted to 5% using DI water in 600 ml beakers and placed in a Crest 40 kHz ultrasonic tank model 4Ht 1014-6. Solutions were heated to 130 F. Twelve preweighed coupons were coated with Precision Finishing Inc, Chemtrol 229 and reweighed. Three coupons were immersed into each solution and cleaned for two minutes. The coupons were rinsed in tap water at 120 F for 30 seconds and dried using a Master Appliance Corp, Hot-air gun model HG-301A at 500 F for 1 minute. Final "clean" weights were recorded and efficiencies were calculated.

Results: Each product removed over 99% of the Chemtrol 229 from the steel coupons in less than 30 seconds. The table below lists the effectiveness for each solution.

Cleaner	Coupon 1	Coupon 2	Coupon 3	Average	Std Dev
Inproclean	99.76	99.28	100.00	99.68	0.37
Daraclean	100.08	99.94	99.79	99.94	0.15
Green Stuff	99.92	99.84	98.43	99.40	0.84
Beyond	99.79	99.90	100.00	99.90	0.11

Summary:

<b>Substrates:</b>		Steel			
<b>Contaminants:</b>		Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Oakite Products	Inproclean 3800	5	99.68	<input checked="" type="checkbox"/>	
Magnaflux	Daraclean 283	5	99.94	<input checked="" type="checkbox"/>	
Bio Chem Systems	Green Stuff 6325	5	99.40	<input checked="" type="checkbox"/>	
Today & Beyond	Beyond 2001	5	99.90	<input checked="" type="checkbox"/>	

Conclusion: All four were successful in removing the burnishing compound from the coupons using ultrasonic energy.