CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2007
DateRun:	05/24/2007
Experimenters:	Shweta Bansal
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Brass
PartType:	Coupon
Contaminants:	Oil
Cleaning Methods:	Ultrasonics
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5 min. Ultrasonics cleaning at 130 F. Rinsing with Tap Water Drying: 30 s50 Air blow off using hose Contaminant 3:1 nPB/Supercoat Substrate 2"x 4"x 0.06" Brass Coupons
Results:	
Summary:	

Substrates:	Brass				
Contaminants:	Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Kyzen Corporation	Ionox HC 2	5	62.15	☐	
Phase III Inc	California Parts Washer Solution	5	5.03	☐	
Florida Chemical Company	Citrus Burst 7	5	-15.93	☐	

Conclusion: