CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2007
DateRun:	06/21/2007
Experimenters:	Shweta Bansal
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Steel
PartType:	Coupon
Contaminants:	Coatings
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5-minute immersion Soak cleaning at 130 F with stir-bar agitation. Rinsing with Tap Water Drying: 30 s50 Air blow off using hose and outlet on bench Contaminant Triethanolamine Substrate 2"x 4"x 0.06" Steel Coupons
Results:	
Summary:	

Substrates:	Steel				
Contaminants:	Coatings				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Warren Chemical Company	Sea Wash Blue	5	100.08	☑	
Gemtek Products	SC Aircraft & Metal Cleaner Super Concentrate	5	100.10	☑	
AG Environmental Products	Soy Gold 2000	5	99.63	☑	

Conclusion: