CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2007
DateRun:	10/29/2007
Experimenters:	Shweta Bansal
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Glass/Quartz
PartType:	Coupon
Contaminants:	Adhesive
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5 min. Immersion Soak cleaning at 130 F with stir-bar agitation. Rinsing with Tap Water Drying: 30 s50 Air blow off using hose and outlet on bench Contaminant Heracus Covercoat L-406 clear Substrate 2"x 4"x 0.06" Glass Coupons

Results:

Summary:

Substrates:	Glass/Quartz				
Contaminants:	Adhesive				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Twin Rivers Technologies	Graffiti Remover	5	-2.98	☐	
Alconox Inc	Citranox	8	7.22	☐	
EcoLink	Safe Strip	5	5.49	☐	
EcoLink	Heavy Weight Non Butyl Detergent	5	6.48	☐	

Conclusion: