

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008
 DateRun: 11/07/2008
 Experimenters: Jason Marshall
 ClientType: Electro-Optical Devices
 ProjectNumber: Project #1
 Substrates: Glass/Quartz
 PartType: Coupon
 Contaminants: Fluxes
 Cleaning Methods: Manual Wipe
 Analytical Methods: Visual

Purpose: To evaluate follow up products on flux removal.

Experimental Procedure: Five products were used at full strength and room temperature for removing the supplied flux. Coupons were coated with two layers of the RMA flux using a handheld swab. The coupons were manually wiped using the same method as previous trials, soaking the rag and wiping the surface. Time to remove the flux was recorded.

Results: All five of the products removed the flux within 10 seconds of the manual wiping. The table lists the amount of time required to remove the flux from the glass surface.

Product	Time
Free & Clear	4 seconds - possible film
Scout Glass & Surface	6 seconds
Kernel Clean	6 seconds - possible film
Clean Environment Glass	5 seconds
SC More Than Glass	7 seconds

Summary:

Substrates:	Glass/Quartz				
Contaminants:	Fluxes				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Seventh Generation	Natural Glass and Surface Cleaner	100		<input checked="" type="checkbox"/>	
Scout Systems	Scout Glass & Surface Cleaner	100		<input checked="" type="checkbox"/>	
Franmar Chemical	Kernel Clean glass cleaner	100		<input checked="" type="checkbox"/>	
The Clean Environment Co	Glass and Hard Surface Cleaner	100		<input checked="" type="checkbox"/>	
Gemtek Products	SC More Than Glass Cleaner	100		<input checked="" type="checkbox"/>	

Conclusion: All five products are good candidates for on-site piloting.