

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008

DateRun: 12/16/2008

Experimenters: Johanna Oviedo

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Buffing/Polishing Compounds

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: To remove silver polish from surface using immersion cleaning

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Products were selected based on the compatibility of substrate and for removal of the contaminant. Five percent concentrations were used and heated the samples at 130F. The coupons were immersed in a product for 5 minutes, rinsed in tap water at 120 F and dried using compressed air at room temperature. Coupons were coated with silver polish using a handheld swab and allowed to dry for 120 minutes at room temperature. The contaminated coupons were weighed again to determine the amount of soil added. After cleaning process, the final weights were recorded, efficiencies were calculated and recorded.

Results:

Cleaner	Initial wt	Final wt	% Removed
Warren Chemical Company, Sea Wash 77			
	0.1794	0.0646	63.99
	0.5656	0.0870	84.62
	0.5122	0.1731	66.20
A 1 Hydro Parke Hill, SW Wash 10			
	0.3957	0.0245	93.81
	0.4295	0.0714	83.38
	0.4371	0.0775	82.27
Kyzen Company, Metalnox CP30			
	0.3151	0.0837	73.44
	0.4564	0.0590	87.07
	0.1348	0.0213	84.20
Kyzen Company, Lonox 1 3302			
	0.7258	0.3062	57.81
	0.9183	0.0998	89.13
	-2.0812	0.0427	102.05
Brulin Corporation, Nonsilicated H TP			
	2.3856	0.0393	98.35
	1.4773	0.0232	98.43
	0.0939	0.0378	59.74
Brulin Corporation, Safety Strip 58			98.00
	0.2490	0.0050	97.99
	0.4646	0.1548	66.68
	0.0256	0.0052	79.69

Summary:

Substrates:	Stainless Steel
Contaminants:	Buffing/Polishing Compounds

CLEANING LABORATORY EVALUATION SUMMARY

Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Warren Chemical Company	Sea Wash 77	5	71.60	<input type="checkbox"/>	
A 1 Hydro Parke Hill Chemical	SW Wash 10 Aircraft Cleaner	5	86.48	<input checked="" type="checkbox"/>	
Kyzen Corporation	Metalnox CP 30	5	81.57	<input type="checkbox"/>	
Kyzen Corporation	Ionox 13302	5	83.00	<input type="checkbox"/>	
Brulin Corporation	Non Silicated HTD	5	85.51	<input checked="" type="checkbox"/>	
Brulin Corporation	Safety Strip 5896 B Oil Seal	5	81.45	<input type="checkbox"/>	

Conclusion: Two products were effective in removing over 85% of the polish using immersion cleaning.