

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2009
 DateRun: 10/19/2009
 Experimenters: Heidi Wilcox, Junhee Cho, Scott Nadolna
 ClientType: Ceramic Coating Company
 ProjectNumber: Project #2
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Waxes
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric
 Purpose: To identify possible alternatives to toluene for manual wax removal.

Experimental Procedure: Nine products were selected from the lab's on-line database, www.cleansolutions.org, based on client supplied information. All were used at room temperature. Five alkaline aqueous cleaners were diluted to 5% using DI water in 300 ml beakers. Four cleaners were used at full strength. Twenty-four preweighed aluminum coupons were coated with wax manually without heat gun and allowed to dry for 24 hours at room temperature. The contaminated coupons were weighed again to determine the amount of soil added. Each cleaner tested with three coupons. Three coupons were placed into a Gardner Straight Line Washability unit. A Kimberly Clark Reinforced paper towel was attached to the cleaning sled and soaked with 5-7 sprays of cleaning solutions. Each coupon was sprayed 3 times with the same cleaning solution. Coupon was cleaned for 18 cycles (~30 seconds) straightly. At the end of the cleaning, coupons were dried at room temperature naturally. Final weights were recorded and efficiencies were calculated and recorded.

Results: Three products were effective in removing the wax with a manual wiping action. The table lists the amount of soil initially added and the amount remaining after cleaning and the product efficiency for each coupon cleaned.

Product	Initial wt	Final wt	% Removed
Buckeye Shopmaster RC			
100%			
	0.0245	0.0009	96.32
	0.0360	0.0008	97.77
	0.0257	0.0015	94.16
Gemtek SC Aircraft metal cleaner			
5%			
	0.0244	0.0029	88.11
	0.0257	0.0036	85.99
	0.0444	0.0089	79.95
Biochem Solsafe 245			
100%			
	0.0425	0.0037	91.29
	0.0381	0.006	84.25
	0.0483	0.0106	78.05
AG Environment Soy Clear 1500			
100%			
	0.0524	0.0181	65.45
	0.0587	0.018	69.33
	0.0405	0.0198	51.11
MacDemid ND LF Supreme			
5%			
	0.0547	0.0163	70.20
	0.0468	0.0184	60.68
	0.0496	0.0185	62.70
Alconox Detergent 8			
5%			
	0.0329	0.0052	84.19

CLEANING LABORATORY EVALUATION SUMMARY

	0.0265	0.0116	56.22
	0.0340	0.0040	88.23
Hurrissafe Hurrissafe 9100 5%			
	0.0449	0.0121	73.05
	0.0397	0.0112	71.78
	0.0362	0.0150	58.56
Activion			
	0.0494	0.0141	71.45
	0.0449	0.0086	80.84
	0.0387	0.0193	50.12
Hurrissafe Hurrissafe S-910 5%			
	0.0315	0.0162	48.57
	0.0318	0.0125	60.69
	0.0592	0.0109	81.58

Summary:

Substrates:	Aluminum				
Contaminants:	Waxes				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Buckeye International	Shopmaster RC	100	95.08	<input checked="" type="checkbox"/>	
Gemtek Products	SC Aircraft & Metal Cleaner Super Concentrate	5	84.68	<input checked="" type="checkbox"/>	
Bio Chem Systems	Solsafe 245	100	84.53	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	61.96	<input type="checkbox"/>	
MacDermid Industrial Products	New Dimensions LF Supreme	5	64.53	<input type="checkbox"/>	
Alconox Inc	Detergent 8	5	76.21	<input type="checkbox"/>	
PCI of America	Hurrissafe 9100 Paint Prep	5	67.80	<input type="checkbox"/>	
Activeion Cleaning Solutions LLC	Activeion Pro	100	67.47	<input type="checkbox"/>	

Conclusion:

Three products (Shopmaster RC, SC Aircraft metal cleaner, Solsafe 245) removed more than 85% of the wax from aluminum coupon. A follow up test will be conducted using longer cleaning times.